

## Synthesis of Hydrous CeO<sub>2</sub> Polypyrrole Nanocomposite as a Rapid and Efficient Adsorbent for Aefluoridation of Drinking Water

Chigondo, Marko Chigondo, Fidelis Nyamunda, Benias

### Abstract

Contamination of water by fluoride ions is one of the major threats to human life and thus must be removed from drinking water. A novel CeO<sub>2</sub> polypyrrole nanocomposite (HCeO<sub>2</sub>@PPy) was fabricated by co-precipitation of CeO<sub>2</sub> nanoparticles followed by *in situ* chemical oxidative polymerization. The as-synthesised adsorbent was characterized using a variety of physico-chemical techniques which included Fourier Transform Infrared Spectroscopy (FTIR), X-Ray diffraction (XRD), Braunauer-Emmett-Teller (BET), Field Emission Scanning Electron Microscopy/Energy Dispersive (FE-SEM/EDS), High Resolution-Transmission Electron Microscopy (HR-TEM), X-ray Photoelectron Spectroscopy (XPS) and point-of-zero charge (pzc) determination. The HCeO<sub>2</sub>@PPy nanocomposite adsorbent was applied for the removal of F<sup>-</sup> ions from aqueous solution. Application of the adsorption modelling, revealed that the Langmuir adsorption isotherm model best described the process with a maximum adsorption capacity of 70.92 mg g<sup>-1</sup>, at an optimum pH of 6.0 ± 0.2, 0.03 g adsorbent dose and 25 °C. Rapid kinetic studies revealed that the pseudo-second-order model gives a better description of the adsorption process. Thermodynamic data showed that the adsorption process was physical, spontaneous and feasible. The behaviour of the amino functional groups within HCeO<sub>2</sub>@PPy moiety and the nanometal oxide surface hydroxides at different pHs along with the pH<sub>pzc</sub>, FTIR and XPS spectra analyses were used to explain the mechanism of adsorption. The mechanism was conceived to be anionic exchange of hydroxyl group with the F<sup>-</sup> ions and electrostatic attractions of protonated hydroxyl on the surface of the adsorbent as well as the nitrogen atoms of amino groups from the polypyrrole (PPy) moiety with F<sup>-</sup> ions. The determined thermodynamic parameters, enthalpy change ( $\Delta H^\circ = -26.33 \text{ kJ mol}^{-1}$ ) and Gibbs free energy change ( $\Delta G^\circ = -19.074 \text{ to } -10.028 \text{ kJ mol}^{-1}$ ) indicated the exothermic and spontaneous nature of the sorption process. Further evaluation on the as-prepared adsorbent exposed a moderately selective material which exhibited excellent removal ability of F<sup>-</sup> ions from ground water at its natural pH to below WHO stipulated levels with an adsorption-desorption efficiency of up to three cycles. Therefore, hydrous CeO<sub>2</sub> polypyrrole nanocomposite has revealed great potential for water defluoridation.

Key Words Polypyrrole, As-synthesised, Thermodynamic, Adsorption